



# Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

**Technical Data** **August, 2016**

**Product Description** 3M™ Scotch-Weld™ Epoxy Adhesives are high performance, two-part epoxy adhesives offering outstanding shear and peel adhesion, and very high levels of durability.

- Features**
- High shear strength
  - High peel strength
  - Outstanding environmental performance
  - Easy mixing
  - 20 minute worklife
  - Controlled flow (3M™ Scotch-Weld™ Epoxy Adhesive DP420 NS Black)
  - Recognized as meeting UL 94 HB – Underwriters Laboratory Horizontal Burn Flammability Test (3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White)
  - Low halogen content (3M™ Scotch-Weld™ Epoxy Adhesive DP420 LH)

**Typical Uncured Physical Properties** **Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

| Product                                  |  | 3M™ Scotch-Weld™ Epoxy Adhesive        |   |  |  |
|--|--|--|---|--|--|
|  |  | DP420 Black                            | DP420 NS Black                          | DP420 Off-White                        | DP420 LH                               |
| <b>Viscosity (approx.) @ 73°F (23°C)</b> | <b>Base Accelerator</b>                        | 20,000-50,000 cP<br>8,000-14,000 cP    | 190,000-270,000 cP<br>60,000-130,000 cP | 20,000-50,000 cP<br>8,000-14,000 cP    | 20,000-50,000 cP<br>8,000-14,000 cP    |
| <b>Base Resin</b>                        | <b>Base Accelerator</b>                        | epoxy<br>amine                         | epoxy<br>amine                          | epoxy<br>amine                         | epoxy<br>amine                         |
| <b>Color</b>                             | <b>Base Accelerator</b>                        | black<br>amber                         | black<br>amber                          | white<br>amber                         | white<br>amber                         |
| <b>Net Weight Lbs./Gallon</b>            | <b>Base Accelerator</b>                        | 9.3-9.7<br>9.0-9.4                     | 9.4-9.8<br>9.1-9.5                      | 9.3-9.7<br>9.0-9.4                     | 9.3-9.7<br>9.0-9.4                     |
| <b>Mix Ratio (B:A)</b>                   | <b>Volume Weight</b>                           | 2:1<br>2:0.97                          | 2:1<br>2:0.97                           | 2:1<br>2:0.97                          | 2:1<br>2:0.97                          |
| <b>Worklife, 73°F (23°C)</b>             | <b>20 g mixed<br/>10 g mixed<br/>5 g mixed</b> | 15 minutes<br>20 minutes<br>30 minutes | —<br>—<br>—                             | 15 minutes<br>20 minutes<br>30 minutes | 15 minutes<br>20 minutes<br>30 minutes |

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

### Typical Cured Properties

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

The properties of cured 3M™ Scotch-Weld™ Epoxy Adhesive DP420 NS Black and 3M™ Scotch-Weld™ Epoxy Adhesive DP420 LH are expected to be similar to the properties of 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black and 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White, respectively as described by data in the following sections of this technical data sheet.

An exception to this is the concentration of halogens in Scotch-Weld DP420 LH. Scotch-Weld DP420 LH is a form of Scotch-Weld DP420 Off-White that can be considered “low halogen”. Low halogen is defined by the Electrotechnical Commission (IEC) 61249-2-21 standard as having less than 900 ppm chlorine, 900 ppm bromine, and less than 1500 ppm total chlorine and bromine.

#### 3M™ Scotch-Weld™ DP420 LH Test Results

| Halogens (determined by ion chromatography) |                     |                      |
|---|---------------------|----------------------|
| Total Chlorine (ppm)                        | Total Bromine (ppm) | Total Halogens (ppm) |
| 720   | <5                  | <800                 |

| Product   | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black     | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White |
|---|---|---|
| <b>Physical</b><br>Color  | Black   | Opaque, off-white                               |
| Shore D Hardness  | 75-80   | 75-80   |
| <b>Thermal</b><br>Coefficient of Thermal Expansion (in./in./°C)     | Below Tg<br>Above Tg                            | Below Tg<br>Above Tg                            |
|   | 80 x 10 <sup>-6</sup><br>194 x 10 <sup>-6</sup> | 85 x 10 <sup>-6</sup><br>147 x 10 <sup>-6</sup> |
| Thermal Conductivity (btu - ft./ft. <sup>2</sup> - hr. - °F) @ 45°C | 0.104   | 0.104   |
| <b>Electrical</b><br>Dielectric Strength (ASTM D 149)               | 888 volts/mil                                   | 690 volts/mil                                   |
| Volume Resistivity (ASTM D 257)                                     | 1.6 x 10 <sup>15</sup> ohm-cm                   | 1.3 x 10 <sup>14</sup> ohm-cm                   |

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

### Typical Curing Characteristics

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

#### Rate of Strength Build-Up

Aluminum, Overlap Shear (7 mil Bondline) (ASTM D 1002-72)

Bonds Tested at 73°F (23°C)

3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black

| Time in Oven | Cure Temperature |                           |                           |
|--------------|------------------|---------------------------|---------------------------|
|              | 73°F (23°C)      | 120°F <sup>1</sup> (49°C) | 140°F <sup>1</sup> (60°C) |
| 15 min.      | —                | —                         | 3200                      |
| 30           | —                | 2300                      | —                         |
| 60           | —                | 4700                      | 4700                      |
| 2 hr.        | 300              | —                         | —                         |
| 3            | 800              | —                         | —                         |
| 5            | 3000             | —                         | —                         |
| 6            | 3700             | —                         | —                         |
| 24           | 4500             | —                         | —                         |

<sup>1</sup>This represents the oven temperature to which the bonds were subjected for the prescribed time. The average bondline temperature during the cure time will be somewhat lower than the oven temperature.

**NOTE:** The data in this data sheet were generated using the 3M™ EPX™ Applicator System equipped with an EPX static mixer, according to manufacturer's directions. Thorough hand-mixing will afford comparable results.

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

### Typical Adhesive Performance Characteristics

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

#### Substrates and Testing

##### A. Overlap Shear (ASTM D 1002-72)

Overlap shear (OLS) strengths were measured on 1 in. wide 1/2 in. overlap specimens. These bonds were made individually using 1 in. x 4 in. pieces of substrate except for aluminum. Two panels 0.063 in. thick, 4 in. x 7 in. of 2024T-3 clad aluminum were bonded and cut into 1 in. wide samples after 24 hours. The thickness of the bondline was 0.005-0.008 in. All strengths were measured at 73°F (23°C) except where noted.

The separation rate of the testing jaws was 0.1 in. per minute for metals, 2 in. per minute for plastics and 20 in. per minute for rubbers. The thickness of the substrates were: steel, 0.060 in.; other metals, 0.05-0.064 in.; rubbers, 0.125 in.; plastics, 0.125 in.

##### B. T-peel (ASTM D 1876-61T)

T-peel strengths were measured on 1 in. wide bonds at 73°F (23°C). The testing jaw separation rate was 20 inches per minute. The substrates were 0.032 in. thick.

##### C. Bell Peel (ASTM D 3167)

Bell peel strengths were measured on 1/2 in. wide bonds at the temperatures noted. The testing jaw separation rate was 6 in. per minute. The bonds are made with 0.064 in. bonded to 0.025 in. thick adherends.

##### D. Cure Cycle

With the exception of Rate of Strength Build-Up Tests, all bonds, were cured 7 days at 73°F (23°C) at 50% RH before testing or subjected to further conditioning or environmental aging.

#### Aluminum, Overlap Shear, at Temperature (PSI)

|                                      | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White |
|--------------------------------------|---|---|
| -67°F (-55°C)                        | 4500  | 4500  |
| 73°F (23°C)                          | 4500  | 4500  |
| 180°F (82°C) (15 min.) <sup>1</sup>  | 1260  | 450   |
| (30 min.) <sup>1</sup>               | 2250  | 700   |
| (60 min.) <sup>1</sup>               | 2980  | 750   |
| (4 hr.) <sup>1</sup>                 | 2690  | 2500  |
| 250°F (121°C) (15 min.) <sup>1</sup> | 570   | 200   |

<sup>1</sup>Represents time in test chamber oven before test.

#### Metals, Overlap Shear, Tested @ 73°F (23°C) (PSI)

|                                    | Scotch-Weld Epoxy Adhesive DP420 Black | Scotch-Weld Epoxy Adhesive DP420 Off-White |
|------------------------------------|--|--|
| Aluminum- Etched                   | 4500                                   | 4500                                       |
| Oakite degrease                    | 4000                                   | 3500                                       |
| MEK/abrade/MEK                     | 2500                                   | 3500                                       |
| Cold Rolled Steel- Oakite degrease | —                                      | 4000                                       |
| MEK/abrade/MEK                     | 2200                                   | 2700                                       |
| Copper- MEK/abrade/MEK             | 5000                                   | 4000                                       |
| Brass- MEK/abrade/MEK              | 2800                                   | 4100                                       |
| Stainless Steel- MEK/abrade/MEK    | 1800                                   | 1700                                       |
| Galvanized Steel- Hot dipped       | 2900                                   | 2000                                       |
| Electrodeposited                   | 3000                                   | 2100                                       |

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

**Typical Adhesive Performance Characteristics**  
(continued)

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

**Substrates and Testing (continued)**

**Aluminum, T-Peel (PIW), at Temperature**

|               | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White |
|---------------|---|---|
| -67°F (-55°C) | 9.3   | 5-10  |
| 73°F (23°C)   | 50  | 50  |
| 180°F (82°C)  | 20  | 3-5   |

**Metals, T-Peel, Tested @ 73°F (23°C) (PIW)**

|                   |                    | Scotch-Weld Epoxy Adhesive DP420 Black | Scotch-Weld Epoxy Adhesive DP420 Off-White |
|-------------------|--------------------|--|--|
| Aluminum, etched  | 17-20 mil bondline | 60                                     | 50   |
|                   | 5-8 mil bondline   | 50                                     | 40   |
| Cold Rolled Steel | 17-20 mil bondline | 40                                     | 40   |
|                   | Oakite degreased   | 25                                     | 25   |
|                   | MEK/abrade/MEK     |  |  |

**Aluminum, Bell Peel (PIW), at Temperature**

|               | Scotch-Weld Epoxy Adhesive DP420 Black | Scotch-Weld Epoxy Adhesive DP420 Off-White |
|---------------|--|--|
| -67°F (-55°C) | 20                                     | not tested                                 |
| 73°F (23°C)   | 82                                     |  |
| 180°F (82°C)  | 18                                     |  |

**Other Substrates, Overlap Shear Tested @ 73°F (23°C) (PSI)**

| Substrate      | Surf. Prep. 1 <sup>1</sup>             |  | Surf. Prep. 2 <sup>2</sup>             |  |
|----------------|--|--|--|--|
|                | Scotch-Weld Epoxy Adhesive DP420 Black | Scotch-Weld Epoxy Adhesive DP420 Off-White | Scotch-Weld Epoxy Adhesive DP420 Black | Scotch-Weld Epoxy Adhesive DP420 Off-White |
| ABS            | 450                                    | 320  | 550                                    | 500  |
| PVC            | 400 <sup>3</sup>                       | 220  | 360 <sup>3</sup>                       | 300  |
| Polycarbonate  | 440                                    | 400  | 450                                    | 550  |
| Polyacrylic    | 190                                    | 230  | 450                                    | 280  |
| Polystyrene    | 380                                    | 350  | 580                                    | 380  |
| FRP            | 600                                    | 350  | 1100 <sup>3</sup>                      | 1300 <sup>3</sup>                          |
| Phenolic       | 1400 <sup>3</sup>                      | 1400 <sup>3</sup>                          | 1300 <sup>3</sup>                      | 1400 <sup>3</sup>                          |
| SBR/Steel      | 70                                     | 150 <sup>3</sup>                           | 180 <sup>3</sup>                       | 150 <sup>3</sup>                           |
| Neoprene/Steel | 80                                     | 40   | 100                                    | 80   |

<sup>1</sup>Isopropyl Alcohol Wipe. See Surface Preparation Section D for additional information.

<sup>2</sup>Isopropyl Alcohol/Abrade/Isopropyl Alcohol: See Surface Preparation Section E for additional information.

<sup>3</sup>Substrate failure.

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

### Typical Adhesive Performance Characteristics (continued)

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

#### Substrates and Testing (continued)

#### Environmental Resistance

#### Aluminum (Etched)

Measured by Overlap Shear Tested @ 73°F (23°C) (PSI)<sup>1</sup> (ASTM D 1002-72)

| Environment                         | Condition  | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black | 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White |
|-------------------------------------|--|---|---|
| 73°F (23°C)/50% RH                  | 30 d <sup>2</sup>  | 4900  | 5100  |
| Distilled Water                     | 30 d, i <sup>3</sup>                                     | 4200  | 4700  |
| Water Vapor                         | 120°F (49°C)/100% RH, 30 d<br>200°F (93°C)/100% RH, 14 d | 4000<br>4000                                | 4700<br>3000                                    |
| Antifreeze/H <sub>2</sub> O (50/50) | 180°F (82°C), 30 d, i                                    | 3000  | 4200  |
| Isopropyl Alcohol                   | 73°F (23°C), 30 d, i                                     | 4500  | 5300  |
| Methyl Ethyl Ketone                 | 73°F (23°C), 30 d, i                                     | 3500  | 4600  |
| Salt Spray (5%)                     | 95°F (35°C), 30 d  | —   | 5100  |
| Skydrol LD-4                        | 150°F (66°C), 30 d, i                                    | 4000  | 5400  |

<sup>1</sup>Data reported are actual values from the lots tested and may be higher than values published elsewhere in this data sheet.

<sup>2</sup> d = days

<sup>3</sup> i = immersion

### 3M™ EPX™ Pneumatic Applicator Delivery Rates

#### 200 ml Applicator – Maximum Pressure 58 psi

| Adhesive*                                       | 6mm Nozzle<br>gms/minute | 10mm Nozzle<br>gms/minute |
|---|--------------------------|---------------------------|
| 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Black     | 29.6                     | 113                       |
| 3M™ Scotch-Weld™ Epoxy Adhesive DP420 Off-White | 31.1                     | 132                       |

\*Tests were run at a temperature of 70°F ± 2°F (21°C ± 1°C) and at maximum applicator pressure.

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

---

### Handling/Application Information

#### Directions for Use

3M™ Scotch-Weld™ Epoxy Adhesive DP420 is supplied in dual syringe plastic duo-pak cartridges as part of the 3M™ EPX™ Applicator System. The duo-pak cartridges are supplied in 37 ml, 200 ml and 400 ml configurations. To use the EPX cartridge system simply insert the duo-pak cartridge into the EPX applicator. Next, remove the duo-pak cartridge cap and expel a small amount of adhesive to be sure both sides of the duo-pak cartridge are flowing evenly and freely. If simultaneous mixing of Part A and Part B is desired, attach the EPX mixing nozzle to the duo-pak cartridge and begin dispensing the adhesive.

When mixing Part A and Part B manually the components must be mixed in the ratio indicated in the typical uncured properties section of this data sheet. Complete mixing of the two components is required to obtain optimum properties.

Two-part mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems are ideal for line uses because of their variable shot size and flow rate characteristics and are adaptable to most applications.

Apply adhesive to clean, dry surfaces, joint parts and secure until adhesive sets (see rate of strength build up).

---

### Surface Preparation

The following surface preparations were used for substrates described in this Technical Data Sheet.

#### A. Aluminum Etch

Optimized FPL Etch - 3M (test method C-2803)

1. Alkaline degrease – Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water (3M test method C-2802).
2. Optimized FPL Etch Solution (1 liter):

| Material          | Amount                                   |
|-------------------|--|
| Distilled Water   | 700 ml plus balance of liter (see below) |
| Sodium Dichromate | 28 to 67.3 grams                         |
| Sulfuric Acid     | 287.9 to 310.0 grams                     |
| Aluminum Chips    | 1.5 grams/liter of mixed solution        |

To prepare 1 liter of this solution, dissolve sodium dichromate in 700 ml of distilled water. Add sulfuric acid and mix well. Add additional distilled water to fill to 1 liter. Heat mixed solution to 66 to 71°C (150 to 160°F). Dissolve 1.5 grams of 2024 bare aluminum chips per liter of mixed solution. Gentle agitation will help aluminum dissolve in about 24 hours.

To FPL etch panels, place them in the above solution at 150 to 160°F (66 to 71°C) for 12 to 15 minutes.

**Note:** Review and follow precautionary information provided by chemical suppliers prior to preparation of this etch solution.

3. Rinse immediately in large quantities of clear running tap water.

# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

---

### Surface Preparation

*(continued)*

4. Dry – air dry approximately 15 minutes followed by force dry at 140°F (60°C) maximum for 10 minutes (minimum).
5. Both surface structure and chemistry play a significant role in determining the strength and permanence of bonded structures. It is therefore advisable to bond or prime freshly primed clean surfaces as soon as possible after surface preparation in order to avoid contamination and/or mechanical damage. Please contact your 3M sales representative for primer recommendations.

#### **B. Oakite Degrease**

Oakite 164 solutions (9-11 oz./gallon of water) at 190°F ± 10°F (88°C ± 5°C) for 2 minutes. Rinse immediately in large quantities of cold running water.

#### **C. MEK/Abrade/MEK**

Wipe surface with a methyl ethyl ketone (MEK) soaked swab, abrade and wipe with a MEK soaked swab.\* Allow solvent to evaporate before applying adhesive.

**\*Note:** When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

#### **D. Isopropyl Alcohol Wipe Only Surface Preparation**

Wipe surface with an isopropyl alcohol soaked swab.\* Allow solvent to evaporate before applying adhesive.

**\*Note:** When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

#### **E. Isopropyl Alcohol/Abrade/Isopropyl Alcohol Surface Preparation**

Wipe surface with an isopropyl alcohol soaked swab, abrade using clean fine grit abrasives, and wipe with an isopropyl alcohol soaked swab.\* Then allow solvent to evaporate before applying adhesive.

**\*Note:** When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.



# 3M™ Scotch-Weld™

## Epoxy Adhesive

DP420 Black • DP420 NS Black • DP420 Off-White • DP420 LH

---

**Storage** Store products at 60-80°F (15-27°C) for maximum shelf life.

---

**Shelf Life** These products have a shelf life of 15 months in original containers at room temperature. Bulk containers have a shelf life of 2 years in their unopened containers.

---

**Precautionary Information** Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

---

**Technical Information** The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

---

**Product Use** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

---

**Warranty, Limited Remedy, and Disclaimer** Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

---

**Limitation of Liability** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**ISO 9001:2008**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.



### Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (Fax)  
[www.3M.com/structuraladhesives](http://www.3M.com/structuraladhesives)

3M, Scotch-Weld and EPX are trademarks of 3M Company.  
©3M 2012 78690097106