

Specification Sheet

SK-10

Super ESKA
Plastic Optical Fiber

High-Performance Plastic Optical Fiber

E s k a™

MITSUBISHI RAYON CO.,LTD.

ESKA OPTICAL FIBER DIVISION

6-41 Konan 1-Chome,Minato-ku,Tokyo,JAPAN

Phone :+81-3-5495-3060

Facsimile:+81-3-5495-3212


1. Scope

The specification covers basic requirements for the structure, optical and mechanical performances of SK-10

2. Structure

Table 1

Item		Specification			
		Unit	Min.	Typ.	Max.
Optical Fiber 1	Core Material	—	Polymethyl-Methacrylate Resin		
	Cladding Material	—	Fluorinated Polymer		
	Core Refractive Index	—	1.49		
	Refractive Index Profile	—	Step Index		
	Numerical Aperture	—	0.5		
	Core Diameter	μm	217	240	263
	Cladding Diameter	μm	227	250	273
Approximate Weight		g/m	0.06		

Sectional View

3. Performances

Table 2

		SK-10				
Item		Acceptance Criterion and/or [Test Condition]	Specification			
			Unit	Min.	Typ.	Max.
Maximum Rating	Storage and Operation Temperature	No Deterioration in Optical Properties*	°C	- 55	-	+70
	Operation Temperature under high humidity	No Deterioration in Optical Properties** [95%RH]	°C	-	-	+60
Optical Properties	Transmission Loss	[650nm Collimated Light] [Standard condition] [10m-1m cutback]	dB/km	-	-	300
Mechanical Characteristics	Minimum Bend Radius	Loss Increment ≤ 0.5 dB [Quarter Bend]	mm	5	-	-
	Tensile Strength	[Tensile Force at Yield Point] [JIS C 6861]	N	3	-	-

All tests are carried out under temperature of 25°C unless otherwise specified.

* Attenuation change shall be within +/- 10% after 1,000 hours.

** Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.